



CHAMPION SEALS (INDIA) PVT. LTD.

Champion Compound, 15 Parsi Panchayat Road, Andheri (East), Mumbai - 400 069.

Tel.: +91-22-28367311 ■ Fax: +91-22-28208686 / 28367316

E-mail : sales@championseals.in ■ www.championseals.in



ASBESTOS FREE RANGE OF PACKINGS, SEALING AND INSULATION PRODUCTS.

CHAMPION Style		Description	pH	Temperature						Size
				°C	Bar	Bar	m/s	Bar	m/s	mm ²
	1	Drylon Packing (Dry PTFE Packing)	0-14	-200 To +280	250	20	10	100	1	3-100
	2	Neoflon Packing (Pure PTFE Packing)	0-14	-210 To +280	240	50	5	150	1	3-100
	3	Ultraflon Packing (Pure PTFE Packing Lubricated)	0-14	-200 To +280	220	20	15	100	2	3-100
	23	Flurocarb Packing (High Tensile PTFE Graphite)	0-14	-250 To +300	350	25	20	250	3	3-100
	36	Graflon Packing (PTFE Graphite Packing)	0-14	-212 To +280	250	25	25	100	3	3-100
	38	Carbosuper (High Purity Carbon Packing)	1-14	-200 To +600	350	75	25	125	2	3-100
	66	Grafosuper (Graphite Filament Packing)	0-14	-100 To +650	350	35	25	150	2	3-100
	172	Duralon Gland Packing (Aramid PTFE Yarn Combination)	2-12	-200 To +280	250	150	10	250	2	3-100
	174	Duralon Mechanical Packing (Aramid Impregnated With PTFE)	3-12	-200 To +300	280	25	25	200	2	3-100
	175	Lubricated Aramid Filament Yarn Packing For High Temperature Applications	1-13	-200 To +300	250	25	25	250	2	3-100
	176	Kombiflon Packing (PTFE - Graphite with Aramid)	3-12	-200 To +300	250	20	25	250	2	3-100
	660	Graphite Packing Ring	0-14	-200°C To 3300°C (Non-Oxidising) -200°C To 600°C (Oxidising) -200°C To 650°C (Steam)	300	100	30	200	3	-
	661	Graphite Self Sealing Ring	0-14		Pressure 300 Bar For Static					
	661M	Graphite Self Sealing Ring - High Pressure	0-14		Pressure 450 Bar For Static					
	663	Graphite Gasket Sheet (1.5 mm / 3 mm)	0-14		40 Bar (Non-Metallic) & 140 Bar (Metallic) for Static					
	664	Pre Cut Pure Graphite Gasket (1.5mm / 3mm)	0-14		40 Bar (Non-Metallic) & 140 Bar (Metallic) for Static					
	668	Pure Graphite Braided Packing	0-14		300	100	25	150	2	3-100
	668 METALLIC	Pure Graphite Braided Packing - With SS or Inconel Wire.	0-14		450	200	15	300	2	3-100

Bar = Operating Pressure. M/S = Velocity



Valve









Rotary Pump



Reciprocating Pump

CHAMPION Style		Description	pH	Temperature						Size
				°C	Bar	Bar	m/s	Bar	m/s	mm ²
	374	Hydroflon Packing (for Hydraulic Applications)	4-10	-40 To+ 150	80	10	7	50	1	3-100
	376	Hydraulic Packing	6-8	-40 to +130	80	10	7	50	1	3-100
	536	PTFE Graphite Hollow Core Packing	0-14	-200 to +300	-	20	20	50	5	3-100
	3116	Graphite Natural Fiber Packing	6-8	-40 to +130	70	10	7	50	1	3-100
	2222	Stern Gland Packing (for Marine Application)	5-9	-40 to +150	220	10	3	100	1	3-100
	2224	Stern Flon Marine Packing	6-10	-40 to +150	240	25	9	100	1	3-100
	3094	PTFE Impregnated Non-Asbestos Packing	3-12	-50 to +280	100	20	5	30	3	3-100
	3800	Self Lubricated Graphite Non-asbestos Packing	0-14	-50 to +300	120	25	10	100	2	3-100
	6094	PTFE Impregnated Synthetic Packing	1-13	Up to +300	100	30	10	100	2	3-100
	6100	Lubricated & Graphited Synthetic Packing	3-10	Up to +300	150	30	-	100	1.5	3-100
	7916	Metallic Ceramic Kiln Seal Rope (with Metal Wire)	0-14	-50° C to +1250° C						

Insulation

	3000	Non Asbestos Inorganic Fiber Packing	0-14	Up to 600° C						
	7000	Ceramic Braided Rope	0-14	Up to 1250° C						
	7012	Ceramic Lagging Rope	0-14	Up to 1250° C						
	7056	Ceramic Yarn	0-14	Up to 1250° C						
	7132	Ceramic Cloth	0-14	Up to 1250° C						
	-	Ceramic Webbing Tape	0-14	Up to 1250° C						

Information in this catalogue is based on our general experience and is given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or is to be implied with respect to such information.